



## METAL KING II (6000A)

### PRODUCT DESCRIPTION

Metal King II ink is designed to give excellent adhesion to stainless steel and uncoated aluminum substrates. It is a single component press-ready ink which offers exceptional mar and chemical resistance.

### RECOMMENDED SUBSTRATES

Metal King II is recommended for use on computer discs, shutters, metal nameplates and signs.

### PHYSICAL PROPERTIES

Solids:	100%
Weight/U.S. Gallon:	9.0 lbs
Viscosity:	6,000-10,000 cps at 25°C
Flash Point:	Greater than 200°F (93°C)
Shelf Life:	6 months at 77°F

### DIRECTIONS FOR USE

Pretest for adhesion to all substrates prior to production printing, as well as, other properties to determine suitability. Mix well prior to each use.

**Surface** - A clean dry surface is preferred for superior adhesion.

**Mesh** - Monofilament polyester or nylon, 350-390 mesh per inch recommended, Acceptable 305-420 mesh per inch. (Open area should not exceed 30%).

**Stencil** - Lacquer proof, most direct or direct/indirect work well.

**Squeegee** - An 80 durometer (Shore A Hardness) polyurethane is recommended. It should be well sharpened.

**Screen Wash Up** - A special high flash point wash containing no hydrocarbon solvents should be used, such as KOLORCURE'S UVW-80 Screen Wash.

**Screening equipment** - Hand, semi-automatic, or fully automatic presses.

### ADDITIVES

To lower the viscosity which will enhance the transfer of the ink through the screen, use Thinner #2 (Diluent).

To increase curing speeds add Activator #7 (Sensitizer).

To eliminate bubbles resulting from the screening process, add Anti-Bubble #2.

To eliminate "fish eyes" in the wet ink film add Flow Promoter.

Use 6100A Mixing Base as an extender to enhance cure and adhesion to substrate.

Use 6400A H/T Mixing Base as an extender to reduce color strength of Process Thickening Powder can be used when color strength can not be altered.

Flattening Powder is available to reduce gloss.

**P  
R  
O  
D  
U  
C  
T  
D  
A  
T  
A  
S  
H  
E  
E  
T**

## **CURING AND CURING EQUIPMENT**

Metal King II inks cure in air upon brief exposure to a focused high intensity ultraviolet light source. A standard 200-300 watt per inch medium pressure mercury vapor lamp should be used. For an optimal cure a 275-325 millijoule window is required. If a loss of gloss or adhesion occurs due to insufficient cure, the use of mixing base will increase light penetration and improve cure. In addition faster curing speeds can also be achieved by adding 3-5% liquid sensitizer.

## **FILM THICKNESS**

Recommended 0.4 to 0.6 mil (10-15 microns).

## **COVERAGE**

Using 390 monofilament polyester mesh, Metal King II will yield an average of 3200 square feet per gallon.

## **STORAGE AND HANDLING**

All KOLORCURE photopolymer inks and coatings should be stored in a cool dry area: 80°F (27°C) or below. Keep these inks and coatings away from direct sun light and indirect white light. Do not use these inks and coatings in areas having fluorescent lights overhead. Keep these inks and coatings away from internal heat sources.

## **SPECIAL NOTES**

All UV inks and coatings are sensitive to contamination. Use only new screens or those previously used for UV printing. Do not add any conventional ink or solvents to the inks. They are most likely not compatible and will destroy all properties.

## **WARNING**

The use of goggles, gloves, and protective clothing is recommended. Avoid prolonged breathing of vapors. Contact of liquid material with the skin may be irritating; wash exposed area thoroughly with soap and water. Contact of liquid with the eyes may cause injury – effects may be delayed; flush eyes with large amounts of water for 15 minutes and call a physician. Like most polymers, the properly –cured resins are considered largely inert.

“Based on our experience, we believe the above information is accurate, but we offer no guarantee as to the use or application of our products or of this information. We warrant our products to be free from defects in material and workmanship; but because their use is beyond our control, we accept no responsibility of liability for damages, whether direct, indirect, or consequential, resulting from failure in performance. In cases where our products are found to be defective in material and workmanship, our liability is limited to the purchase price of the products found to be defective. THIS WARRANTY IS TO THE EXCLUSION OF ALL OTHER WARRANTIES OR GUARANTEES, EXPRESSED OR IMPLIED, AS TO MERCHANTABILITY, FITNESS FOR ANY PARTICULAR PURPOSE, DESCRIPTION, PRODUCTIVENESS OR ANY OTHER MATTER. None of the above information may be construed as recommendation that our products be used in violation of any rights. We accept our orders at our shipping points only on the basis of the above understanding which our employees have no authority to vary.”