



## SERIES 7100 CONTAINER DÉCOR (71-000)

### PRODUCT DESCRIPTION

Series 7100 is a press-ready UV ink formulated specifically for the container decorating industry. Properly cured, these inks will exhibit excellent adhesion and superior resistance to solvents, water, and chemicals typically packaged in these containers. Other important features include flexibility and fast curing during high speed printing.

### RECOMMENDED SUBSTRATES

Series 7100's adhesion to treated Polyethylene, Polypropylene, PVC, PET, and many other packaging substrates is excellent.

### PHYSICAL PROPERTIES

Solids:	100%
Weight/U.S. Gallon:	9.0 lbs
Viscosity:	4000-8000 cps at 25°C
Flash Point:	Greater than 200°F (93°C)
Shelf Life:	6 months at 77°F

### DIRECTIONS FOR USE

Pretest for adhesion to all substrates prior to production printing, as well as, other properties to determine suitability. Mix well prior to each use.

**Surface** - A clean dry surface is preferred for superior adhesion.

**Mesh** - Monofilament polyester or nylon, 350-390 mesh per inch recommended, Acceptable 305-420 mesh per inch. (Open area should not exceed 30%).

**Stencil** - Lacquer proof, most direct or direct/indirect work well.

**Squeegee** - An 80 durometer (Shore A Hardness) polyurethane is recommended. It should be well sharpened.

**Screen Wash Up** - A special high flash point wash containing no hydrocarbon solvents should be used, such as KOLORCURE'S UVW-80 Screen Wash.

**Screening equipment** - Hand, semi-automatic, or fully automatic presses.

### ADDITIVES

To lower the viscosity which will enhance the transfer of the ink through the screen, use Thinner #1 (Diluent) OR #2.

To increase curing speeds add Activator #7 (Sensitizer).

To eliminate bubbles resulting from the screening process, add Anti-Bubble #2.

To eliminate "fish eyes" in the wet ink film add Flow Promoter.

Use 71-100 Mixing Base as an extender to enhance cure and adhesion to substrate.

Use 71-400 H/T Mixing Base as an extender to reduce color strength of Process colors and to increase the viscosity of standard colors for fine line copy.

Thickening Powder can be used when color strength can not be altered.

Flattening Powder is available to reduce gloss.

**P  
R  
O  
D  
U  
C  
T  
  
D  
A  
T  
A  
  
S  
H  
E  
E  
T**

## **CURING AND CURING EQUIPMENT**

Series 7100 has been formulated for fast curing to maximize production speeds. Focused mercury vapor arcs and microwave lamps with a window of 200-225 millijoules will provide an optimal cure. Printing speeds of 70-100 bottles per minute can be expected.

## **FILM THICKNESS**

Recommended 0.4 to 0.6 mil (10-15 microns).

## **COVERAGE**

Using 390 monofilament polyester mesh, Series 7100 will yield an average of 3200 square feet per gallon.

## **STORAGE AND HANDLING**

All KOLORCURE photopolymer inks and coatings should be stored in a cool dry area: 80°F (27°C) or below. Keep these inks and coatings away from direct sun light and indirect white light. Do not use these inks and coatings in areas having fluorescent lights overhead. Keep these inks and coatings away from internal heat sources.

## **SPECIAL NOTES**

All UV inks and coatings are sensitive to contamination. Use only new screens or those previously used for UV printing. Do not add any conventional ink or solvents to the inks. They are most likely not compatible and will destroy all properties.

## **WARNING**

The use of goggles, gloves, and protective clothing is recommended. Avoid prolonged breathing of vapors. Contact of liquid material with the skin may be irritating; wash exposed area thoroughly with soap and water. Contact of liquid with the eyes may cause injury – effects may be delayed; flush eyes with large amounts of water for 15 minutes and call a physician. Like most polymers, the properly –cured resins are considered largely inert.

“Based on our experience, we believe the above information is accurate, but we offer no guarantee as to the use or application of our products or of this information. We warrant our products to be free from defects in material and workmanship; but because their use is beyond our control, we accept no responsibility of liability for damages, whether direct, indirect, or consequential, resulting from failure in performance. In cases where our products are found to be defective in material and workmanship, our liability is limited to the purchase price of the products found to be defective. THIS WARRANTY IS TO THE EXCLUSION OF ALL OTHER WARRANTIES OR GUARANTEES, EXPRESSED OR IMPLIED, AS TO MERCHANTABILITY, FITNESS FOR ANY PARTICULAR PURPOSE, DESCRIPTION, PRODUCTIVENESS OR ANY OTHER MATTER. None of the above information may be construed as recommendation that our products be used in violation of any rights. We accept our orders at our shipping points only on the basis of the above understanding which our employees have no authority to vary.”